



Plant 1

Start 1/Jan/2014

End 31/Dec/2014

Production Summary Report

Work Tank		Production %	No. of Cycles	Total Treated Volume	Average	Chemical Usage (based on Charge Reports)
Green	100	790	9410.8	11.91	8000	10485.49
						TANAGARD 173.92
						kg

Use Class Summary										
	No. of Cycle:	Treated Volume	Average Charge	Injection l/m ³	Actual Target	%	Cycle Pressure			
3/GFaFE	4	52.92	13.23	66	58	114	98.6	27.3		
2/BI	597	7192.97	12.05	31	50	62	94.5	15.3		
3/BX	6	69.25	11.54	44	56	79	113.6	31.3		
4/GFB	61	644.28	10.56	52	196	27	155.6	61.3		
2/TB	11	107.6	9.78	37	52	71	254	14.9		
3/GFa	111	1343.78	12.11	60	100	60	110.1	29.5		

Plant Utilisation											
N°	790	Charges completed	Operator	Will	56	Kevin	733	Arch Service	1	Average time in Auto	101.2 mins
										Average Cycle time	103.8 mins

LONZA
Lonza Wood Protection

auto-treater®

Defoamer 0.0 Litres

TANAGARD 341.6 Litres

TANALITH E Concentrate 19168.0 Litres

Water 657800.0 Litres

No. of Mixes 512

End 31 December 2014

Start 01 January 2014

WOOD PRESERVATIVE



Mix Summary

Date 22/12/2014
Time 10:39
Operator Kevin
Plant 1
Work Tank 1